

Product Speksifikasi (Product Specification)

**BELCEM**

**F&W GROUT**



Category	Cementitious (Sanded) Fine Coloured Grout
Composition	Portland Cement, Mineral Aggregates, Organic Additives
Performance	Confirm to BS 5385 : Part 1 - 4
Water Absorption Rate	½ hours – 4.80%
	4 hours – 5.00%
Shrinkage Value	0.05% (72 hours)
Flexural Strength	9.70 N/mm <sup>2</sup>
Compressive Strength	31.50 N/mm <sup>2</sup>
Tensile Bonding Strength	Dry : 1000 N
	Wet : 920 N
Working Time (Pot Life)	45 minutes
Setting Time	24 hours
Type of Tile	Ceramic, Homogeneous, Porcelain Tile
Area	Internal, external, dry or wet
Joint Width	3 – 12 mm wide

